


Gap Pad™ VO

Conformable, Thermally Conductive Material for Filling Air Gaps


Gap Pad VO is a thermally conductive cost effective material that acts as a thermal interface between a heat sink and an electronic device. The conformable nature of Gap Pad VO allows the pad to fill in air gaps between PC boards and heat sinks or a metal chassis.

Gap pad VO is a conformable silicone polymer filled with alumina on a fiberglass carrier. The material is available in thickness from 0.020" to 0.250" with a removable liner applied to the light pink side of the material. The range in thickness and the materials flexibility allow Gap Pad VO to be used in a variety of applications where surface texture vary and the space between surfaces is uneven. The material is available in die-cut parts and sheets. Standard sheet size is 8" X 16", with or without adhesive.

To calculate the approximate amount of deflection for a specific material thickness, at a given pressure, refer to the graph below. Multiply the thickness of the material by the percentage at the given pressure.*



The resultant thickness of the Gap Pad will determine the thermal resistance. Subtracting the initial gap pad thickness by the deflection value, obtained above, will give the resultant thickness. Refer to the graph below to obtain the thermal resistance of the material.



Typical Properties of Gap Pad VO

Property	Typical Value	Test Method
Color	Gold / Pink	Visual
Thickness	0.020" to 0.250"	ASTM D374
Specific Gravity	1.6 g/cc	ASTM D792
Heat Capacity	1.0 J/g-K	ASTM C351
Hardness (Shore Type 00)	<u>Thickness</u>	<u>Hardness</u>
	.020" - .250"	80 - 40
Young's Modulus psi (1)	<u>Modulus</u>	<u>Rate</u>
	100	0.01"/min.
Continuous Use Temp.	-60°C to 200°C	
Electrical		
Dielectric Breakdown Voltage	>6 kV	ASTM D149
Dielectric Constant	5.5	ASTM D150
Volume Resistivity	10 ¹¹ Ohm-meter	ASTM D257
Flame Rating	94 V-O	U.L.
Thermal		
Thermal Conductivity	0.8 W/m-K	ASTM D5470

- (1) Graphs and data generated from Young's Modulus, calculated using 0.01 inch/min. step rate of strain with a sample size of 0.79 inch². For more information on Gap Pad modulus refer to Bergquist Application Note #116.

Rev: Jan. 24. 2001



The Bergquist Company
North American Headquarters
18930 West 78th Street
Chanhassen, MN 55317
Phone: 800-347-4572
Fax: 952-835-4156

The Bergquist Company-Europe
Bramenberg 9a
3755 BT Eemnes
Netherlands
Phone: 31-35-5380684
Fax: 31-35-5380295

The Bergquist Company-Asia
6F, No. 1, Alley 7, Lane 113, Sec. 3
Min Sheng East Road
Taipei, Taiwan, ROC 105
Phone: 886-2-8712-6220
Fax: 886-2-8712-6219

All statements, technical information and recommendations herein are based on tests we believe to be reliable, and THE FOLLOWING IS MADE IN LIEU OF ALL WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MARKETABILITY AND FITNESS FOR PURPOSE. Sellers' and manufacturers' only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and the user assumes all risks and liability whatsoever in connection therewith. NEITHER SELLER NOR MANUFACTURER SHALL BE LIABLE EITHER IN TORT OR IN CONTRACT FOR ANY LOSS OR DAMAGE, DIRECT, INCIDENTAL, OR CONSEQUENTIAL, INCLUDING LOSS OF PROFITS OR REVENUE ARISING OUT OF THE USE OR THE INABILITY TO USE A PRODUCT. No statement, purchase order or recommendations by seller or purchaser not contained herein shall have any force or effect unless in an agreement signed by the officers of the seller and manufacturer.