

Nylon Tubing Series T, TIA

For general air tubing **Nylon tubing**

Burst Pressure Characteristics Curve



Series Table




▲ Precautions

Caution

- 1) Applicable for general industrial water. Consult SMC if using for other kinds of fluid. Surge pressure must be under the max. operating pressure. If exceeding that value, fitting may be damaged and tubing may be burst.
- 2The value of the max. operating pressure is at a temperature of 20°C. Refer to the burst pressure characteristics curve for other temperatures. Avoid abnormal temperature rise which may burst the tubing.
- 3The values of the min. bending radius is at a temperature of 20°C and O.D. variable rate 10% max. In case that operating temperature is higher than 20°C, O.D. variable rate may be over 10% even if bending radius is within the specified range.

How to Order



Made to Order

BU

G

Blue

Yellow

Green

1) 100m roll for Metric size (black, white, red, blue, yellow, green) and Inch size (black, white, red, blue, yellow, green)

Suffix "-X3" to the end of part number. Ex.) T0425R-100-X3

* Consult SMC in case of ø16.

2 20m roll for Inch size (except black and white)

Suffix "-X4" to the end of part number. Ex.) TIA01BU-20-X4

3 Longer roll length (black, white, red, blue, yellow, green)

Suffix "-X3" to the end of part number. Ex.) T0425B-500-X3


* Available 150m for ø10, 200m for ø8, 500m for ø4 and ø6. Contact SMC for other lengths.



Soft Nylon Tubing Series TS, TISA

For general air pressure **Pliable**

Burst Pressure Characteristics Curve



⚠ Precautions


⚠ Caution

- 1. Compatible with water due to a change in materials. Compatible fluid types are printed on the tube body for differentiation, so please be sure to check this. Note) If using the previous TS/TISA series with "water", the tube may shrink and cause air leakage or the tube may fall out.
- 2. Please exercise caution when using this item in a clean room. There is a possibility of plasticizer and other materials precipitating on the tube surface and detracting from the cleanliness level of the room.
- 3. The value of the minimum bending radius is measured at the temperature of 20°C as shown in the figure below.



Bend the tube into U-form at a temperature of 20°C. Fix one end and close loop gradually. Measure 2R when the tube breaks or is crushed.

Series Table



How to Order

S0604 100 Indication of tube Length per roll model Symbol Colour indication 20

Symbol Colour

В	Black
W	White
R	Red
BU	Blue
Υ	Yellow
G	Green

20m roll 100m roll (Black and white only)

Roll size

100

Made to Order

1) 100m roll for Metric size (black, white, red, blue, yellow, green) and Inch size (black, white, red, blue, yellow, green)

Suffix "-X3" to the end of part number. Ex.) TS0604BU-100-X3

* Consult SMC in case of ø16

2 20m roll for Inch size (except black and white)

Suffix "-X4" to the end of part number. Ex.) TISA01BU-20-X4

3 Longer roll length (black, white, red, blue, yellow, green)

Suffix "-X3" to the end of part number. Ex.) TS425B-500-X3


* Available 150m for Ø10, 200m for Ø8, 500m for Ø4 and ø6. Contact SMC for other lengths.



Polyurethane Tubing Series TU, TIUB

Forgeneralairpressuretubing
Orange colour now becomes
standard
100m roll available for all
color types

Burst Pressure Characteristics Curve




Series Table	!							●: 20m	roll □:	100m roll
					Tube	size				
		Metric s	size (Sei	ries TU)			Inch	size (Se	ries TIU	B)
Model	TU0425	TU0604	TU0805	TU1065	TU1208	TIUB01	TIUB05	TIUB07	TIUB11	TIUB13
Tube O.D. (mm)	4	6	8	10	12	3.18	4.76	6.35	9.53	12.7
Tube I. D. (mm)	2.5	4	5	6.5	8	2	3.18	4.23	6.35	8.46
Black (B)	-					•	•	•	- ∳-	_∳_
White (W)										_
Red (R)		_								_
Blue (BU)						•	•	•	-	- ∳-
Yellow (Y)	-									
Green (G)										
Clear (C)		_								
Orange (YR)										
]			Nomi	nal size	(inch)	
	5/32 "		5/16 "			1/8 "	3/16 "	1/4 "	3/8 "	1/2 "
Specifications		'		,						
Fluid		-		Δ	ir, Wate	r				
Max. operating pressure				0.81	/IPa at 2	0°C				
Burst prssure		Refer to pressure characteristics curve.								
Min. bending radius (mm)	10	15	20	27	35	10	15	23	27	35
Operating temperature		-2	0 to +60	°C (Wate	er: 0 to 4	10°C) (N	o freezir	ng)		
Material				Po	lyuretha	ne				

⚠ Precautions

①Applicable for general industry water. Consult SMC if using for other kinds of fluids. Surge pressure must be under the max. operating pressure. If exceeding that value, fitting may damaged and tubing may burst.

- ②The value of the max. operating pressure is at a temperature of 20°C. Refer to the burst pressure characteristics curve for other temperatures. Avoid abnormal temperature rises which may burst the tubing.
- 3The values of the min. bending radius is at a temperature of 20°C. Higher temperatures allows the tubing to bend more.

How to Order



 Symbol
 Roll size*

 20
 20m roll

 100
 100m roll

20

Made to Order

1 100m roll for Metric size (black, white, red, blue, yellow, green) and Inch size (black, white, red, blue, yellow, green)

Suffix "-X3" to the end of part number. Ex.) TIUB01Y-100-X3

* Consult SMC in case of ø16.

② 20m roll for Inch size (except black and white)

Suffix "-X4" to the end of part number. Ex.) TIUB01Y-20-X4

3 Longer roll length (black, white, red, blue, yellow, green)

Suffix "-X3" to the end of part number. Ex.) TU0425B-500-X3

 Available 150m for ø10, 200m for ø8, 500m for ø4 and ø6. Contact SMC for other lengths.



Soft Polyurethane Tubing


Series TUS



Suitable for piping in confined spaces **Extremely flexible** Soft Polyurethane Tubing

TUS related accessories Inner Sleeve Series TJ

Reinforces soft polyurethane tubing. Insert an inner sleeve into soft polyurethane tubing when used with a One-touch fitting.



Part No.	Applicable tube model	Length
TJ-0425	TUS0425	18
TJ-0604	TUS0604	19
TJ-0805	TUS0805	20.5
TJ-1065	TUS1065	23
T.I-1208	TUS1208	24

Specifications

Material	C2700T (Nickel plated)
Wall thickness	0.2mm

⚠ Precautions

- ①Use nylon or polyurethane tubing for general industry water to prevent the tubing from coming out or bursting due to possibility of surge pressure generation.
- 2 The value of the max. operating pressure is at a temperature of 20°C. Refer to the burst pressure characteristics curve for other temperatures. Avoid abnormal temperature rise which may burst the tubing.
- 3The value of the min. bending radius is at a temperature of 20°C. Higher temperatures allows the tubing to bend more.
- 4 Use inner sleeve taking the removing force into consideration when used with Onetouch fittings.

Sorios Tablo

Series Table				●: 20m ro	II □: 100m roll
Model	TUS0425	TUS0604	TUS0805	TUS1065	TUS1208
Tube O.D. (mm)	4	6	8	10	12
Tube I.D. (mm)	2.5	4	5	6.5	8
Black (B)	—				
White (W)	—				
Red (R)					
Blue (BU)	—				<u> </u>
Yellow (Y)					
Green (G)					
Opaque (N) (1)					
Yellow brown (YB)	—				
Specifications					

-										
Fluid					Α	ir				
Max. operating p	oressure			0	.6MPa	at 20°0	2			
Burst pressure		R	efer to	burst p	ressure	chara	cteristi	cs curv	e.	
Applicable tube	fitting	One	e-touch	fitting,	Insert t	ube fitt	ing, Ho	se nip	ple ⁽³⁾	
Min. bending rad	dius (mm) (2)	8 15 15 22 29					9			
Operating temper	erature		•	–20 to	+60°C	(No fre	ezing)		•	
Material					Polyur	ethane				
Tube drawing strenght N	Without inner sleeve	15 60 60				0	8	5	11	0
(Using One-touch fitting)	With inner sleeve	80	23	30	25	50	30	00	48	30

Note1) Not clear but opaque due to material.


Note2) Min. bending radius is measured as shown in the figure below.




Bend the tube into U-form at a temperature of 20°C. Fix one end and close loop gradually. Measure 2R when the tube breaks or is crushed.

Note3) Always use inner sleeve (Series TJ) in safety circuit or critical area.


Burst Pressure Characteristics Curve






Hard Polyurethane Tubing

Series TUH



Maximum effective area increased nearly 44% TUH/Standard Type

(Compared to polyurethane tubing TU0805: O.D. 8mm, length 1m)



Tubing in	nside diameter co	mparisoı	า			(mm)			
Tu	ıbing O.D. (ØD1)	4 6 8 10 12							
Tubing	TUH/Standard type	2.8	4.4	5.8	7.3	8.8			
I.D. (ØD2)	TUH/High pressure type	2.5	4	5	6.5	Ω			
	TU	2.5	4	5	0.5	0			

Operating pressure 1.0MPa (at 20°C) TUH/High Pressure Type

Has the same operating pressure as series TS soft nylon tubing, and a bending radius equivalent to series TU polyurethane tubing.

Can be restored even after folding


Restoration is outstanding compared to nylon tubing, leaving no creases from folding.



Hard Polyurethane Tubing/Standard Type

Series TUH





At a temperature of 20°C bend the tubing into a U shape. Then with one side fixed, gradually close the other side and measure 2R at the point where the tubing folds or flattens, etc.

Series



Model	TUH0428	TUH0644	TUH0858	TUH1073	TUH1288
O.D. mm	4	6	8	10	12
I.D. mm	2.8	4.4	5.8	7.3	8.8
Black (B)					
White (W)					
Blue (BU)		-		-	—
Translucent (N)	-	_ •	-	-	—
Specification	ons				

Fluid Max. operating pressure (at 20°C) Min. bending radius mm 10 18 24 30 36 Burst pressure Refer to the burst pressure characteristics curve.

Burst pressure Refer to the burst pressure characteristics curve.

Operating temperature -20 to 60°C

Material Polyurethane

Note 1) Consult SMC regarding other fluids.

Water cannot be used due to the occurrence of hydrolysis.


Note 2) The maximum operating pressure is the value at 20°C. Refer to the burst pressure


characteristic curve for other temperatures.

Furthermore, an abnormal temperature increase due to adiabatic compression can cause tubing to burst.

Note 3) The minimum bending radius is measured at 20°C using the method shown in the figure at the left. At higher temperatures, breakage or flattening, etc., may occur at more than the minimum bending radius.

Burst Pressure Characteristic Curve and Operating Pressure








Hard Polyurethane Tubing/High Pressure Type

Series TUH





At a temperature of 20°C bend the tubing into a U shape. Then with one side fixed, gradually close the other side and measure 2R at the point where the tubing folds or flattens, etc.

Series

● – 20m bundle □ – 100m bundle

Model	TUH0425	TUH0604	TUH0805	TUH1065	TUH1208
O.D. mm	4	6	8	10	12
I.D. mm	2.5	4	5	6.5	8
Black (B) White (W) Blue (BU) Translucent (N)					
Specification	ons				
Eluid		_	Air Note 1)	_	

Florid								
Fluid	Air Note 1)							
Max. operating pressure (at 20°C)	1.0MPa Note 2)							
Min. bending radius mm	10 15 20 27 35							
Burst pressure	Refer	to the burst	pressure cha	racteristics	curve.			
Operating temperature	−20 to 60°C							
Material			Polyurethane	1				

Note 1) Consult SMC regarding other fluids.


Water cannot be used due to the occurrence of hydrolysis.


Note 2) The maximum operating pressure is the value at 20°C. Refer to the burst pressure characteristic curve for other temperatures.

Furthermore, an abnormal temperature increase due to adiabatic compression can cause tubing to burst.

Note 3) The minimum bending radius is measured at 20°C using the method shown in the figure at the left. At higher temperatures, breakage or flattening, etc., may occur at more than the minimum bending radius.

Burst Pressure Characteristic Curve and Operating Pressure







Series TUH/Specific Product Precautions 1

Be sure to read before handling.

Precautions on Usage


⚠ Caution

- Water cannot be used due to the occurance of hydrolysis.
 Use nylon or polyurethane tubing for general industrial water.
 Furthermore, consult SMC regarding use with any fluids other than air.
- The maximum operating pressure is the value at 20°C. Refer to the burst pressure characteristic curve for other temperatures.
 Furthermore, an abnormal temperature increase due to adiabatic compression can cause tubing to burst.
- The minimum bending radius indicates the value at which the tubing will fold at a temperature of 20°C. At higher temperatures, the tubing may fold at more than the minimum bending radius.
- 4. Store away from direct sunlight in a location at no more than 40°C





FEP Tubing (Fluoropolymer)



• Heat resistance: 200°C
It changes according to the operating pressure.
Refer to the graph of the max. operating pressures on page 1.

4 Colour variations



8 Size variations

Metric size: ø4 to ø12

Applicable fittings

One-touch fittings (Series KQ2,KJ)
Miniature fittings (Series M,MS) (Hose nipple type)
Insert fittings (Series KF)
High Purity Fluoropolymer fittings (Series LQ)

Series TH

Applications

General pneumatic piping

Food
Semiconductor
Medical care
Automobile


 Certified to current Food Sanitation Legislation

Ministry of Japanese Health and \
Safety, directive #370,1959

FEP Tubing (Fluoropolymer) Series TH




How to measure the minimum bending radius.



At a temperature of 20°C, bend the tubing into a U shape. Fix one end and gradually move the other end closer. Measure 2R at the point where the outside diameter's rate of change is 5%.

Max. Operating Pressure



Note) The maximum operating pressure varies dependant on the I.D. bore size even if the O.D. is the same.

Series ●-20m roll □-100m roll Metric size Model TH0402 TH0425 TH0604 TH0806 TH1075 TH1008 TH1209 TH1210 Tubing O.D. (mm) Tubing I.D. (mm) 2 2.5 7.5 10 Colour Symbol Translucent Ν R Red (Translucent) BU Blue (Translucent) В Black (Opaque) Inch nominal size Inch nominal size

Specifications Fluid Air, Water Note 1), Inert gas One-touch fittings: Series KQ, KJ Insert fittings: Series KF Note 2) **Applicable** Fluoropolymer fittings: Series LQ fittings Miniature fittings: Series M, MS (Hose nipple type) Refer to below "Max. Operating Pressure." Max. operating pressure Min. bending 15 20 35 95 100 130 radius (mm) Operating temperature Air, Inert gas: -20 to 200°C Water: 0 to 100°C (No freezing) FEP (Fluorinated Ethylene Propylene Resin)

5/16"

Note 1) When using a fluid in liquid form, the surge pressure must not exceed the maximum operating pressure. A surge pressure higher than the maximum operating pressure can cause breakage of the fittings, or rupture of the tubing. Furthermore, an abnormal temperature increase due to adiabatic compression can also result in ruptured tubing. Note 2) Do not use in locations where the FEP tubing will move.

Be sure to operate under the maximum operating pressure conditions using the lower maximum operating specification of either the tubing or fittings.

After long term use or under high temperatures, some fittings leakage may occur due to material deterioration with age. Perform periodic inspections, and if any leakage is detected, replace with a new product immediately. (Refer to maintenance part of "Tubing Precautions 1" on the page 7-156.)


Refer to Best Pneumatics 4 in "Fittings and Tubing" for all other precautions.

5/32"

For High Purity Fluoropolymer, refer to the precautions of CAT. ES70-17, "High Purity Fluoropolymer Fittings & Tubing."

Note 3) Minimum bending radius is measured as shown left as representative values.

Allow extra length when piping since the tubing may crush if bent more than the min. bending radius. Note 4) Consult SMC if using any other fluids.







Chemical Resistance of the Fluoropolymer FEP Material

Chemicals in this table are inactive against FEP material Note 1), however physical properties may be effected by temperature or pressure change.

Please make sure that operating conditions do not cause problems since the use of FEP tubing under chemical environment is unsecured.

2-nitro-2-methyl propanol

2-nitrobutanol

Pentabasic benzamide

N-butylamine N-octadecanol N-butyl acetate O-cresol

Di-isobutyl adipate Acetophenone

Acetone Alniline Abietic acid

Sulphuric chloride

Isooctane

Liquid ammonia Ethyl alcohol Ethyl ether Ethylene alvcol Ethylenediamine Zinc chloride Aluminum chloride Ammonium chloride

Calcium chloride Sulphuric chloride Iron chloride (III) Benzovl chloride Magnesium chloride Hydrochloric acid

Chlorine (absolute) Aqua regia Ozone

Hydrogen peroxide Natrium peroxide

Gasoline Permanganate Formic acid Xvlene

Chromic acid

Chlorosulfonic acid Chloroform

Paraffinum liquidum

Allyl acetate Ethyl acetate Potassium Butyl acetate

Sodium hypochlorite Carbon tetrachloride

Dioxane

Cyclohexanone Cyclohexane Dimethyl ether Dimethylsulfoxide

Dimethylformamide Bromine

Deionized water Nitric acid

Mercury

Ammonium hydroxide Potassium hydroxide

Sodium hydroxide

Cetane

Soap, detergent Dibutyl sebacate Diethyl carbonate Tetrachloroethylene Tetrahydrofuran Tetrabromoethane Triethanolamine Trichloroethylene Trichloroacetic acid

Toluene Naphtha Naphthalene Naphthol Lead

Carbon dioxide Nitrogen dioxide Nitrobenzene Nitromethane Perchloroethylene Perphloroxylene

Unsymmetrical dimethylhydrazine

Hvdrazine Pinene **Piperidine**

Glacial acetic acid (Acetic acid)

Pyridine Phenol Phthalic acid Dybutyl phthalate

Dimethyl phthalate Hydrofluoric acid Naphthalene fluoride

Nitrobenzene fluoride

Furan

Hexachlorethane

Hexane

Boric acid

Ethyl hexanoate Phenylcarbinol Benzaldehyde Benzonitrile Borax

Formic aldehyde (Formalin)

Acrylic anhydride Acetic anhydride Methacrylic acid Allyl methacrylate Vinyl methacrylate Methyl alcohol Methyl ethyl ketone Methylene chloride Sulphuric acid Phosphoric acid Iron phosphate (III) Tri-n-butyl phosphate

Tricresyl phosphate

Note 1) "Inactive in chemistry terminology" means - not to cause any chemical reaction.

Reference cited: Teflon®, the fluoropolymer handbook, Manual for the chemical applications of Teflon®. Du Pond-Mitsui Fluorochemicals Co., Ltd.

Teflon® is a registered trademark for the fluoropolymer produced by E.I du Pond de Nemours & Company (Inc.) and Du Pond-Mitsui Fluorochemicals Co., Ltd.

Selection

⚠ Warning

1. Confirm the specifications.

The products appearing in this catalogue are designed for use only in compressed air systems (including vacuum).

Do not use outside the specified ranges of pressure, temperature, etc., as this may cause damage or malfunction. (Refer to specifications.)

SMC cannot assure the product quality when fluids other than air, water and inert gas are used.

Consult with SMC for details.

2. In case of using the product for medical care

This product is designed for use with compressed air system applications for medical care purposes. Do not use in contact with human bodily fluids, body tissues or transfer applications to a human living body.

⚠ Caution

 Do not use in locations where the connecting threads and tubing connection will slide or rotate. The connecting theads and tubing connection will come apart under these conditions.

Use rotary type one-touch fittings (Series KS, KX) in cases where sliding or rotation will occur. Only air can be used as the operating fluid, when using rotary type one-touch fittings.

- Use tubing at or above the minimum bending radius. Using below the minimum bending radius can cause breakage or flattening of the tubing.
- Never use the tubing for anything flammable, explosive or toxic such as, gas, fuel gas, or cooling mediums, since the contents can penetrate outward.

Mounting

⚠ Caution

- Before mounting confirm the model and size, etc. Also, confirm that there are no blemishes, nicks or cracks in the product.
- When tubing is connected, consider factors such as changes in the tubing length due to pressure, and allow sufficient leeway.
- Mount so that fittings and tubing are not subjected to twisting, pulling or moment loads. This can cause damage to fittings and flattening, bursting or disconnection of tubing, etc.
- Mount so that tubing is not damaged due to tangling and abrasion. This can cause flattening, bursting or disconnection of tubing, etc.

Piping

⚠ Caution

1. Preparation before piping

Before piping is connected, it should be thoroughly blown out with air (flushing) or washed to remove chips, cutting oil and other debris from inside the pipe. Do not allow chips of the piping thread or the seal material to go in.

Air Supply

⚠ Warning

1. Types of fluid

This product is designed for use with compressed air. Consult SMC if a different fluid is to be used.

Consult SMC regarding products for use with general purpose fluids, to confirm which fluids can be used.

2. When there is a large amount of drainage.

Compressed air containing a large amount of drainage can cause the malfunction of pneumatic equipment. An air dryer or Drain Catch should be installed upstream from filters.

3. Drain management

If air filter drains are not flushed regularly, the drainage will flow downstream leading to the malfunction of pneumatic equipment.

In cases where the management of drain flushing will be difficult, the use of filters with automatic drains is recommended.

For details on the quality of compressed air mentioned above, refer to SMC's "Best Pneumatics" catalogue vol. 4.

Operating Environment

$oldsymbol{\Delta}$ Warning

- 1. Do not operate in locations in an explosive atmosphere.
- 2. Do not operate in locations where vibration or impact occurs.
- 3. In locations near heat resources, block off radiant heat.

Maintenance

$oldsymbol{\Lambda}$ Caution

- Check for the following during regular maintenance, and replace components as necessary.
 - a) Scratches, gouges, abrasion, corrosion
 - b) Leakage
- c) Twisting, flattening or distortion of tubing
- d) Hardening, deterioration or softness of tubing
- 2. Do not repair or patch the replaced tubing or fittings for reuse.
- 3. When using insert or miniature fittings over a long period, some leakage may occur due to age deterioration of the materials. Perform periodic inspections, and if any leakage is detected, correct the problem by additional tightening. If tightening becomes ineffective, replace the fittings with a new product immediately.




Polyurethane Coil Tubing

Series TCU



For flexible tubing Compact piping possible

Burst Pressure Characteristics Curve




Specifications

Model	TCU 0425B-1	TCU 0425B-2	TCU 0425B-3	TCU 0604B-1	TCU 0604B-2	TCU 0604B-3	TCU 0805B-1	
Number of tubes	1	2	3	1	2	3	1	
Tube O.D. (mm)		4			6		8	
Tube I.D. (mm)		2.5			4		5	
Fluid				Air (1)				
Max. operating pressure (2)			0.8	MPa at 20	°C			
Burst prssure		Refe	er to press	ure charac	teristics cu	ırve.		
Operating temperature			-2	0 to +60°C)			
Material		Polyurethane						
Colour				Black				

Note 1) Consult SMC if using for other fluids than air.

Note 2) Refer to burst pressure characteristics curve for other temperatures. Avoid abnormal temperature rises.

Dimensions



^{*} Dimensions are changeable due to material.

Made to Order (Consult SMC for detailed specifications, dimensions and delivery.) Change of coil turns, Color change (Max. operating length) 100 100 Tube fastener (Multi-tube only)

	Spec.	Tube siz	ze (mm)	nm) Coil (mm)				Max. operating	
Part No		O.D.	I.D.	L	øD	tubes	per tube length	length (mm)	
TCU042	5□-1- N -X6			N X 4	18	1	3 to 90	L X 5.9 + 200	
TCU042	5□-2-N-X6	4	2.5	N X 8	28	2	3 to 90	L X 4.4 + 200	
TCU042	5□-3- N -X6			N X 12	28	3	3 to 63	L X 2.9 + 200	
TCU060	4□-1- N -X6			N X 6	24	1	3 to 90	L X 5.3 + 200	
TCU060	4□-2-N-X6	6	4	N X 12	37	2	3 to 66	L X 3.8 + 200	
TCU060	4□-3-N-X6			N X 18	37	3	3 to 44	L X 2.5 + 200	

Spec.	Tube siz	ze (mm)	Coil (mm)		No. of	No. coil windings	Max. operating
Part No.	O.D.	I.D.	L	øD	tubes	per tube length	length (mm)
TCU0805□-1-N-X6	8	5	N X 8	31	1	3 to 90	L X 5.2 + 200
TCU0805□-2-N-X6	8	5	N X 16	42	2	3 to 40	L X 3 + 200
TCU1065□-1-N-X6	10	6.5	N X 10	52	1	3 to 45	L X 5 + 200
TCU1065□-2-N-X6	10	0.5	N X 20	52	2	3 to 35	L X 3 + 200
TCU1208□-1-N-X6	12	8	N X 12	67	1	3 to 35	L X 5 + 200
TCU1208□-2-N-X6	12	ď	N X 24	67	2	3 to 30	L X 3 + 200

^{□ →} B (Black), W (White), R (Red), BU (Blue), Y (Yellow), G (Green), C (Clear), YR (Orange)



N → Coil turns


Polyurethane Flat Tubing

Series TFU



Compact piping possible

Burst Pressure Characteristics Curve



Specifications


Part No.	TFU 0425B-2	TFU 0425B-3	TFU 0604B-2	TFU 0604B-3	TFU 0805B-2	TFU 0805B-3	
Number of tubes	2	3	2	3	2	3	
Tube O.D. (mm)	4	4 6		6		3	
Tube I.D. (mm)	2.5 4 5				5		
Fluid	Air (1)						
Max. operating pressure (2)	0.8MPa at 20°C						
Burst prssure	Refer to burst pressure characteristics curve						
Operating temprature	-20 to +60°C (No freezing)						
Material	Polyurethane						
Colour	Black						
Min. bending radius (mm)	1	0	1	5	2	0	
Tube length per roll (m)			1	0			

Note1) Consult SMC if using for other fluids than air.

Note2) Refer to burst pressure characteristics curve for other temperatures.

Avoid abnormal temperature rises.

How to Order



Made to Order

(Consult SMC for detailed specifications, dimensions and delivery.)

1 Colour change (10m roll)

Suffix "X4" to the end of part number. Ex.) TFU0604BU-2-10- $\overline{\text{X4}}$


• W: White, R: Red, BU: Blue, Y: Yellow, G: Green, C: Clear, YR: Orange (All tubes are same colour.)

② Longer roll length (50m or 100m roll)

Suffix "X3" to the end of part number. Ex.) TFU0425B-2-50- $\overline{X3}$

3 Number of tubes (10m roll)

Suffix "X4" to the end of part number. Ex.) TFU0604B-4-10-X4



Flame Resistance (Equivalent to UL-94 Standard V-0)


FR Soft Nylon Tubing

Series TRS



Applicable for general air pressure and water in a spark atomosphere such as spotwelding. Flame resistance tube

Burst Pressure Characteristics Curve




Series Table			● : 20m roll	☐: 100m roll				
Model	TRS0603	TRS0805	TRS1065	TRS1208				
Tube O.D. (mm)	6	8	10	12				
Tube I.D. (mm)	3	5	6.5	8				
Black (B)	•							
White (W)	•	•	<u> </u>	•				
Red (R)		•	<u> </u>	•				
Blue (BU)		•	<u> </u>	<u> </u>				
Green (G)		•	<u> </u>	<u> </u>				
Specifications								
Fluid		Air, V	Vater					
Max. operating pressure		1.2MPa	at 20°C					
Burst pressure	Refer	to burst pressure	e characteristics curve.					
Min. bending radius (mm)	17	19	27	32				
Operating temperature	-20 to	-20 to +60°C (Water: 0 to 60°C)(No freezing)						
Material Flame resistance nylon (UL-94 Standard V-0)								

APrecautions

①Applicable for general industry water. Consult SMC if using for other kinds of fluid. Surge pressure must be under the max. operating pressure. If exceeding that value, fitting may be damaged and tubing may be burst.

- ②The value of the max. operating pressure is at a temperature of 20°C. Refer to the burst pressure characteristics curve for other temperatures. Avoid abnormal temperature rises which may burst the tubing.
- 3The value of the min. bending radius is at a temperature of 20°C and O.D. variable rate 10% max. In case that operating temperature is higher than 20°C, O.D. variable rate may be over 10% even if bending radius is within the specified range.



Flame Resistance (Equivalent to UL-94 Standard V-0)

FR Double Layer Tubing

Series TRB

Suitableforairandwaterpipingin environments where sparks from spot welders, etc., may be a problem.


Double layer design using flame resistantresin(equivalenttoUL-94 Standard V-0) for outer layer.



Series Table ●: 20m roll □: 100m roll Model TRB0604 TRB0806 TRB1075 TRB1209 Inner tube O.D. (mm) 10 12 7.5 Inner tube I.D. (mm) 4 6 9 Outer layer thickness (mm) 1 1 Black (B) White (W) Outer Red (R) • layer Blue (BU) • • • colour

Green (G)				
Minimum bending (4) radius (mm)	15	28	35	45

Specifications





Yellow (Y)

Note1) The colour of all inner tube is black.


Note2) Applicable for general industry water. Consult SMC if using for other kinds of fluid. Surge pressure must be under the max. operating pressure.


Note3) Refer to burst pressure characteristics curve for other temperatures. Avoid abnormal temperature rises.

Note4) The value for a temperature of 20°C and O.D.variable rate 10% max.

Inner tube Outer layer FR double layer tubing (sectional view)

Burst Pressure Characteristics Curve








FR Double Layer Tubing Series TRB


How to Install to One-touch Fitting

⚠ Caution

Length of tube to be inserted into One-touch fitting is indicated on the outer layer of TRB tubing.

Cut the tube according to this indication. (Procedure ①) and then strip off the outer layer. (Procedure ②) for installing tube.







Strip off outer layer

⚠ Precautions


⚠ Caution

- ①Applicable for general industrial water. Consult SMC if using for other kinds of fluid. Surge pressure must be under the max. operating pressure. If exceeding that value, fitting may be damaged and tubing may be burst.
- ②The value of the max. operating pressure is at a temperature of 20°C. Refer to the burst pressure characteristics curve for other temperatures. Avoid abnormal temperature rises which may burst the tubing.
- 3The value of the min. bending radius is at a temperature of 20°C and O.D. variable rate 10% max. In case that operating temperature is higher than 20°C, O.D. variable rate may be over 10% even if bending radius is within the specified range.

Flame Resistant (Equivalent to UL-94 Standard V-0) FR Double Layer Polyurethane tubing

Series TRBU





Series Table



	Model	TRBU0604	TRBU0805	TRBU1065	TRBU1208
Inter	nal tube O.D. mm	6	8	10	12
Inter	nal tube I.D. mm	4	5	6.5	8
Exte	rnal layer thickness mm	1	1	1	1
Note 1)	Black (B)		<u></u>		
² 05	White (W)		•	-	
ауе	Red (R)		•	-	—
al la	Blue (BU)		•	-	—
Note 1) External layer colour	Yellow (Y)		•	-	—
ũ	Green (G)			-	—
	Note 4)				
Minimum bend 15		5	20	27	35

Specifications

F	luid	Air, Water Note 2)				
Maximum operating Note 3) pressure (at 20°C)		0.8MPa {8.2kgf/cm²}				
Burst pres	sure	Refer to burst pressure characteristics curve				
Ambient ar		-20 to 60°C For water 0 to 40°C (without freezing)				
Materials	Internal tube	Polyurethane				
iviater lais	External layer	PVC (equivalent to UL-94 standard V-0)				

Note 1) The colour of all internal tubes is black.


Note 2) Can be used with general industrial water. Contact SMC if used with other fluids.


Also keep surge pressure at or below the maximum operating pressure.

Note 3) In case of other temperatures, refer to the burst pressure characteristics curve. In addition, operate so that abnormal temperature rise due to adiabatic compression does not occur.

Note 4) Indicates the bending value of the tubing at a temperature of 20°C .

Burst Pressure Characteristics Curve and Operating Pressure








FR Double Layer Polyurethane Tubing Series TRBU

Installation on One-touch Fittings

⚠ Caution

Since the pitch length for installation on a One-touch fitting is indicated on the external layer of TRBU tubing, cut the tubing according to this indication (Step 1), strip off the external layer only (Step 2), and then install on the One-touch fitting.



Precautions on Useage

⚠ Caution

- Useage is possible with general industrial water. Contact SMC if product will be used with other fluids. Also, keep surge pressure at or below the maximum operating pressure. If surge pressure exceeds the maximum operating pressure, this can cause damage to fittings or bursting of the tubing.
- 2. The maximum operating pressure is the value when at 20°C. In case of other temperatures, refer to the burst pressure characteristics curve. Furthermore, bursting of the tubing can be caused by an abnormal temperature rise due to adiabatic compression.
- 3. The minimum bend radius indicates the bending value of the tubing at a temperature of 20°C. The tubing may bend beyond the minimum bend radius at higher temperatures.
- 4. Tubing should be stored in a location out of direct sunlight and at 40°C or below.

SMC

Antistatic Tubing

Series TA

Conductive tubing prevents troubles caused by static electricity.


Antistatic soft nylon tubing/Series TAS

For air pressure piping to product or assembly while preventing static electricity.

Flame resistant tube (UL-standard, V-0)




Burst Pressure Characteristics Curve



Series Table				●:2	0m roll 🔲 :	100m roll
Model	TAS3222	TAS0425	TAS0604	TAS0805	TAS1065	TAS1208
Tube O.D. (mm)	3.2	4	6	8	10	12
Tube I.D. (mm)	2.2	2.5	4	5	6.5	8
Black (B)	—					
Specifications Max. operating pressure (1)			1.2MPa at	+ 30°C		
-		Dofor to bur			20 0118/0	
Burst pressure	Refer to burst pressure characteristics curve.					Г
Min. bending radius (mm) ⁽²⁾	12	12	15	19	27	32
Operating temperature	0 to 40°C					
Material	Conductiv	e nylon + Fl	ame resista	nt nylon (UL	-94standard	l, V-0)
Surface resistance	10^4 to $10^7\Omega$					

Note1) Refer to burst pressure characteristics curve for other temperatures. Avoid abnormal temperature rises. Note2) The value at temperature of 20°C and O.D. variable rate 10% max.

How to Order




<u>Antistatic polyurethane tubing/Series TAU</u>

For air pressure piping to product or assembly while preventing static electricity.

Flexible tube



Burst Pressure Characteristics Curve



Series Table				● : 20m r	oll □: 10	0m roll
Model	TAU3220	TAU0425	TAU0604	TAU0805	TAU1065	TAU1208
Tube O.D. (mm)	3.2	4	6	8	10	12
Tube I.D. (mm)	2	2.5	4	5	6.5	8
Black (B)	—					
Specifications May appeting agreeurs (1)			O OMPo o	10000		
Max. operating pressure (1)		- · · ·	0.9MPa a			
Burst pressure	ı	Refer to burs	st pressure o	characteristic	cs curve.	
Min. bending radius (mm) ⁽²⁾	10	10	15	20	27	35
Operating temperature			0 to 40)°C		
Material	Conductive polyurethane					
Surface resistance	10^4 to $10^7\Omega$					

Note1) Refer to burst pressure characteristics curve for other temperatures. Avoid abnormal temperature rises.

Note2) The value at temperature of 20°C.

